SECURITY CLASSIFICATION OF THIS PAGE

REPORT DOCUMENTATION PAGE

AD-A242 571

E
991
D
C

	1b. RESTRICTIVE MARKINGS
	3. DISTRIBUTION / AVAILABILITY OF REPORT Approved for public release; distribution unlimited
4. PERFORMING ORGANIZATION REPORT NUMBER(S) Report # 3	5. MONITORING ORGANIZATION REPORT NUMBER(S)
6a. NAME OF PERFORMING ORGANIZATION Washington University 6b. OFFICE SYMBOL (If applicable)	7a. NAME OF MONITORING ORGANIZATION Office of Naval Research
6c. ADDRESS (City, State, and ZIP Code) One Brookings Drive St. Louis, MO 63130-4899	7b. ADDRESS (City, State, and ZIP Code) 800 N. Quincy Street Arlington, VA 22217-5000
8a. NAME OF FUNDING / SPONSORING ORGANIZATION ONR 8b. OFFICE SYMBOL (If applicable)	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER N00014-90-J-4118; R&T Code (413MØØ1)
8c. ADDRESS (City, State, and ZIP Code) 800 N. Quincy Street Arlington, VA 22217-5000	10. SOURCE OF FUNDING NUMBERS PROGRAM ELEMENT NO. / PROJECT NO. / TASK NO. / WORK UNIT ACCESSION NO

11. TITLE (Include Security Classification)

Molecular Dynamics of Polycarbonate Chains at the Interface of Polycarbonate/Polystyrene Heterogeneous Blends

12. PERSONAL AUTHOR(S)
Mobae Afeworki and Jacob Schaefer

13a. TYPE OF REPORT	13b. TIME COVERED	14. DATE OF REPORT (Year, Month, Day)	15. PAGE COUNT
Technical	FROM _____ TO _____	11/14/91	17

16. SUPPLEMENTARY NOTATION

17. COSATI CODES			18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)
FIELD	GROUP	SUB-GROUP	DNP-selected; spin-echo ^{13}C NMR; interfacial-PC; PC/PS blends; motion.

19. ABSTRACT (Continue on reverse if necessary and identify by block number)

As monitored by DNP-selected dipolar rotational, spin-echo ^{13}C NMR, interfacial-PC chains in thin-film PC/PS blends have less motion than PC chains in the bulk.

20. DISTRIBUTION / AVAILABILITY OF ABSTRACT	21. ABSTRACT SECURITY CLASSIFICATION	
☒ UNCLASSIFIED/UNLIMITED ☐ SAME AS RPT ☐ DTIC USERS		
22a NAME OF RESPONSIBLE INDIVIDUAL Dr. Jacob Schaefer	22b TELEPHONE (Include Area Code) 314-935-6844	22c. OFFICE SYMBOL

DD FORM 1473, 84 MAR 83 APR edition may be used until exhausted
All other editions are obsolete

SECURITY CLASSIFICATION OF THIS PAGE

III. Molecular Dynamics of Polycarbonate Chains at the Interface of Polycarbonate/Polystyrene Heterogeneous Blends

Mobae Afeworki† and Jacob Schaefer

Department of Chemistry
Washington University
St Louis, MO 63130



†Present Address: Exxon Research and Engineering Company, Annandale NJ 08801

ABSTRACT

As monitored by DNP-selected dipolar rotational, spin-echo ^{13}C NMR, interfacial-PC chains in thin-film PC/PS blends (see previous paper for notation) have less motion than PC chains in the bulk.

INTRODUCTION

Having generated and identified a ^{13}C NMR signal arising exclusively from PC chains near the PC/PS interface, we can now perform NMR relaxation experiments to characterize the microscopic dynamics of these chains. A difference pulse sequence is used similar to that shown in Figure 5 (I), but which includes a period for carbon dephasing under the influence of dipolar coupling to protons isolated from one another by multiple-pulse H-H decoupling [1]. Thus, the full experiment involves monotoring the dephasing of DNP-enhanced ^{13}C NMR magnetization of interface-PC chains in a thin-film PC/PS blend by dipolar rotational spin-echo (DRSE) ^{13}C NMR [2]. The results of DRSE experiments have been well established for the characterization of the molecular chain dynamics of synthetic polymers [2-8] and proteins [9,10].

EXPERIMENTS

DNP-Selected DRSE ^{13}C NMR: A semi-windowless MREV-8 sequence [11] was coupled with DNP CPMAS ^{13}C NMR for DRSE experiments with DNP selection (Figure 1). The DNP-difference part of the experiment selects the PC chains at the interface of the PC/PS blend. In the first half of this alternate-block, pulse sequence, the carbon magnetization is prepared with a 1.0-second microwave irradiation at the difference of the electron and proton Larmor frequencies. The resulting DNP-enhanced proton magnetization is transferred to carbons by a standard cross-polarization technique (1.0-ms matched spin-lock contact at 50 kHz). In the second half of the experiment, the carbon magnetization is prepared just with the standard cross-polarization transfer; the microwave irradiation is delayed until after ^{13}C data acquisition has been completed. Each acquisition is a two-rotor-period experiment in which the evolution of the carbon magnetization due to chemical-shift effects is refocused by a ^{13}C 180° pulse applied at the end of the first rotor period.

During the first rotor period of each half of the experiment, immediately after the cross-polarization contact, protons are decoupled from carbons by an 87-kHz rf field. The H-H multiple-pulse decoupling is applied for a variable time during the second rotor period following the carbon 180° refocusing pulse. This results in a two-dimensional NMR experiment [12] during one time dimension of which, carbon magnetization is allowed to evolve under C-H coupling while H-H interactions are suppressed by semi-windowless MREV-8 decoupling. The accumulated signal from the first half of the experiment is subtracted from that of the second half.

The semi-windowless MREV-8 H-H multiple-pulse decoupling was composed of eight 3.0-μs pulses with four windows [13-15] of 2.4 μs each for a total cycle time, t_c, of 33.6 μs. The 87-kHz 3-μsec pulses were slightly larger than 90° for better refocusing [16]. Sixteen MREV-8 cycles exactly fit into one rotor period with 1859-Hz magic-angle sample spinning. However, in some experiments, the number of the MREV-8 cycles varied from zero (no MREV-8 pulses during the second rotor period) to only eight. This truncation avoided the burden of an excessively long experiment on the klystron. Because the time-domain data is symmetrical [2], the data corresponding to the ninth to fifteenth MREV-8 cycles can be constructed from that for the zeroth to eighth MREV-8 cycles. The percent refocusing is the ratio of the intensities of the carbon signals obtained experimentally with a full sixteen MREV-8 cycles to that obtained with zero MREV-8 cycles. Typically, 70-80% percent of the protonated aromatic-carbon signal of PC refocused. Full refocusing is not possible because of incomplete H-H decoupling [3,17]. A 16-point Fourier transform was used to produce a 16-point dipolar frequency spectrum [18] with the imaginary buffer set equal to zero. For an isolated ^{1}H-^{13}C spin pair, the pure absorption spectrum is a symmetrical dipolar Pake pattern [19] broken into spinning sidebands [20].

Carr-Purcell NMR: Cross-polarization, magic-angle spinning echo amplitudes were measured using a rotor-synchronized, Carr-Purcell refocusing sequence (Figure 2). Following a standard H-C cross-polarization transfer at 50 kHz, carbon magnetization is allowed to evolve for an integral number of rotor periods, nT_r. This is followed by a ^{13}C 180° chemical-shift refocusing pulse. Signal detection starts 2n rotor periods

after the completion of the cross-polarization transfer [21]. A 50-kHz C-H dipolar decoupling field was used throughout the evolution and detection periods. The Carr-Purcell experiment was performed on a total of four samples all based on PC(^{13}C): two polycarbonates and two thin-film blends. The polycarbonates were PC(^{13}C) and a physical mixture of PC(^{13}C) and BDPA, denoted by PC(^{13}C)/*. The thin-film blends used were the PC(^{13}C)/PS(^{12}C/*) and PC(^{13}C)/PS(^{2}D/*) samples whose preparation is described in I.

DRSE Echo Refocusing: Following a ^{13}C inspection pulse the carbon magnetization was allowed to evolve under chemical shift *only* and under combined chemical-shift and C-H dipolar interactions. The magnetization was sampled 16 times each rotor period. The details of these experiments and results on homogeneously doped PC will be discussed in IV. In this paper, only the results on PC and inhomogeneously-doped PC obtained under the combined chemical-shift and C-H dipolar interactions will be presented. These results demonstrate the effect of aggregated BDPA on the degree of carbon magnetization refocused under the application of H-H multiple-pulse decoupling.

RESULTS

DNP-Selected DRSE ^{13}C NMR: The time evolution of the ^{13}C magnetization of the ^{13}C-labeled, protonated, aromatic carbons of PC at the interface of the thin-film PC/PS blend, PC(^{13}C)/PS(^{12}C/*), is shown in Figure 3. The DRSE data for the protonated, aromatic carbons of bulk PC and the protonated,

aromatic carbons of bulk PS are also shown in the same figure. The intensity of the ^{13}C magnetization is plotted as a function of the number of semi-windowless MREV-8 cycles used in the H-H multiple-pulse decoupling. The plots are normalized so that the first points of all three curves match. The decay of the interface-PC magnetization is intermediate to those for bulk PC and bulk PS.

Linewidths by Carr-Purcell NMR: Spin-echo ^{13}C NMR spectra of PC(^{13}C), PC(^{13}C)/*, PC(^{13}C)/PS(^{12}C/*), and PC(^{13}C)/PS(^{2}D/*) are shown in Figure 4. The stacked plots are of chemical shift versus the number of rotor periods, n, preceding the refocusing π pulse (see Figure 2). The observed homogeneous linewidths, obtained from the echo decays are 34, 50, 38, and 52 Hz for PC(^{13}C), PC(^{13}C)/*, PC(^{13}C)/PS(^{12}C/*), and PC(^{13}C)/PS(^{2}D/*), respectively.

DRSE Echo Refocusing: Figure 5 shows the time-domain evolutions of ^{13}C magnetization under combined chemical-shift and C-H dipolar interactions, with H-H interactions suppressed by MREV-8 pulses for PC(^{13}C) and PC(^{13}C)/*. These data were obtained by a synchronous-detection experiment. Details of the experiment will be presented in IV. The first point (with t = 0 defined by the top of the first echo) of both curves is adjusted to have the same magnitude. Both samples have rotational echoes arising from the refocusing of chemical-shift and dipolar interactions. The echo train of PC(^{13}C/*) decays faster than that of PC(^{13}C). After one rotor period the refocusing for PC(^{13}C) and PC(^{13}C)/* is 74% and 62%, respectively.

DISCUSSION

DNP-Selected DRSE ^{13}C NMR: After the application of only one cycle of semi-windowless MREV-8 pulses the ^{13}C magnetization of bulk PS decreases by about 25%, whereas that of bulk PC decreases by only about 10%. Moreover, the ^{13}C magnetization of the bulk PS is substantially negative after only three semi-windowless MREV-8 cycles, while that of bulk PC is barely negative after five MREV-8 cycles. We know that restricted molecular motion results in fast DRSE dephasing of ^{13}C magnetization [18]. Because aromatic-carbon magnetization in bulk PS dephases faster than that in bulk PC, the PS aromatic carbons have less motion than the PC aromatic carbons. The faster dephasing for bulk PS is attributed primarily to the absence of averaging of C-H dipolar interactions by π flips about the ring C_2 axis [18].

The dephasing of the ^{13}C magnetization of the DNP-selected interfacial-PC signal is intermediate to that of bulk PC and bulk PS (Figure 3). Thus, the interfacial-PC aromatic carbons have less motion than bulk PC aromatic carbons, but more motion than bulk PS aromatic carbons. This reduction of interface-PC motion relative to bulk-PC motion can be explained in terms of the interference with cooperative, interchain motions. Presumably, the dense, or at least atypical, packing of PC chains near the impenetrable PS barrier [22] inhibits the lattice dilation necessary to enable a ring π flip [23].

DRSE and Carr-Purcell Refocusing: The presence of free radicals in PC broadens ^{13}C-resonance lines and reduces the efficiency of MREV-8 decoupling. The free radicals do not have to be molecularly dispersed in the PC chains to produce these effects. Inhomogeneous mixing of BDPA with PC to make PC(^{13}C)/* reduces the refocusing in both DRSE and Carr-Purcell echo experiments (Figures 4 and 5). Because the DNP-selected DRSE ^{13}C NMR experiments on blends were performed on narrow lines arising from protonated, aromatic carbons not affected by molecularly dispersed BDPA and not close to aggregated BDPA, the appropriate control for the DRSE dephasing is bulk PC chains in PC homopolymer (Figure 3), not bulk PC chains in PC(^{13}C)/PS(^{12}C/*). In the latter sample, some PC chains are near BDPA aggregates and so are subject to local susceptibility variations.

ACKNOWLEDGEMENT

This work has been supported by the Office of Naval Research under contract N00014-88-K-0183.

REFERENCES

1. Waugh, J.S.; Huber, L.M.; Haeberlen, U. *Phys. Rev. Lett.*, **1968**, *20*, 180.
2. Schaefer, J.; McKay, R.A.; Stejskal, E.O.; Dixon, W.T. *J. Magn. Reson.*, **1983**, *52*, 123.
3. Schaefer, J.; Stejskal, E.O.; McKay, R.A.; Dixon, W.T. *Macromolecules*, **1984**, *17*, 1479.
4. Poliks, M.D.; Schaefer, J. *Macromolecules*, **1990**, *23*, 3426.
5. Garbow, J.R.; Schaefer, J. *Macromolecules*, **1987**, *20*, 819.
6. Schaefer, J.; Sefcik, M.D.; Stejskal, E.O.; McKay, R.A.; Dixon, W.T.; Cais, R.E. *Macromolecules*, **1984**, *17*, 1107.
7. Poliks, M.D.; Schaefer, J. *Macromolecules*, **1990**, *23*, 2682.
8. Poliks, M.D.; Gullion, T.; Schaefer, J. *Macromolecules*, **1990**, *23*, 2678.
9. Garbow, J.R.; Jacob, G.S.; Stejskal, E.O.; Schaefer, J. *Biochemistry*, **1989**, *28*, 1362.
10. Bork, V.; Gullion, T.; Hing, A.; Schaefer, J. *J. Magn. Reson.*, **1990**, *88*, 523.
11. Burum, D.P.; Linder, M.; Ernst, R.R. *J. Magn. Reson.*, **1981**, *44*, 173.
12. Munowitz, M.G.; Griffin, R.G. *J. Chem. Phys.*, **1982**, *76*, 2848.
13. Mansfield, P. *J. Phys.*, **1971**, C4, 1444.
14. Rhim, W.K.; Elleman, D.D.; Vaughan, R.W. *J. Chem. Phys.*, **1973**, *58*, 1772.
15. Rhim, W.-K.; Elleman, D.D.; Schreider, L.B.; Vaughan, R.W. *J. Chem. Phys.*, **1974**, *60*, 4595.
16. Haeberlen, U. in *High Resolution NMR in Solids, Selective Averaging*, Academic Press, New York, **1976**, Chap. 5.

17. Schaefer, J.; Sefcik, M.D.; Stejskal, E.O.; McKay, R.A. *Macromolecules*, **1981**, *14*, 280.

18. Schaefer, J. in *New Directions in Chemical Analysis: Characterization of Solid Polymers by C-13 NMR*, Texas A & M Univ. Press, **1985**, p.396.

19. Pake, G.E. *J. Chem. Phys.*, **1948**, *16*, 77.

20. Mericq, M.M.; Waugh, J.S. *J. Chem. Phys.*, **1979**, *70*, 3300.

21. Sefcik, M.D.; Schaefer, J.; Stejskal, E.O.; McKay, R.A. *Macromolecules*, **1980**, *13*, 1132.

22. Kumar, S.K.; Vacatello, M.; Yoon, D.Y. *Macromolecules*, **1990**, *23*, 2189.

23. Walton, J.H.; Lizak, M.J.; Conradi, M.S.; Gullion, T.; Schaefer, J. *Macromolecules*, **1990**, *23*, 416.

FIGURE CAPTIONS

Figure 1. Pulse sequence for dipolar rotational spin-echo ^{13}C NMR of carbons selected by DNP difference. Proton-proton decoupling is done using a semi-windowless MREV-8 sequence. The position of the 180° pulse is synchronized with the end of the first rotor period. Data acquisition begins at the end of the second rotor period. The accumulated signal from the first half of the experiment is subtracted from that of the second half.

Figure 2. Pulse sequence for cross-polarization, magic-angle spinning spin-echo ^{13}C NMR.

Figure 3. The time evolution of the DRSE ^{13}C NMR signal of the protonated, aromatic-carbon magnetization of *homopolymer bulk PS*, *homopolymer* bulk PC, and interfacial PC of a thin-film PC/PS blend. The interface-PC signal is obtained from the *difference* spectra of chains selected by DNP ^{13}C CPMAS NMR using the pulse sequence of Figure 1. Data points are connected for clarity. The relatively fast dephasing of the interfacial-PC signal indicates that PC chains at the interface are more restricted than those in bulk.

Figure 4. Cross-polarization, magic-angle spinning, rotational-echo ^{13}C NMR spectra of PC(^{13}C), lower left; PC(^{13}C)/*, upper left; PC(^{13}C)/PS(^{12}C/*), lower right; and PC(^{13}C)/PS(^{2}D/*), upper right. These two-dimensional stacked spectra are obtained by plotting the chemical-shift as a function of the number of rotor periods, n, using the pulse

sequence of Figure 2. The peaks around δ_C 0 and 250 are spinning sidebands.

Figure 5. Rotational echoes of PC(^{13}C) and PC(^{13}C)/* under a combination of chemical-shift and dipolar interactions. The refocusing of the rotational echoes is affected by the presence of inhomogeneously mixed BDPA. The horizontal dashed lines represent the echo amplitude of PC(^{13}C) at the end of the second rotor period. The top of the first echo defines the left-hand side of each plot.

Figure 1


ADD
electron
H
C
rotor
CP
H-C decouple
H-H decouple
π
Acquire
0
1
2
SUBTRACT
electron
H
C
rotor
CP
H-C decouple
H-H decouple
π
Acquire
0
1
2

Figure 2



Figure 3


1.0
0.8
0.6
0.4
0.2
0
-0.2
0
2
4
6
8
PROTONATED AROMATIC-CARBON MAGNETIZATION
bulk polycarbonate
interface polycarbonate
bulk polystyrene
TIME (number of 33.6-μsec mutiple-pulse decoupling cycles)


ROTOR-SYNCHRONIZED HAHN ECHO
PC(13C)/*
PC(13C)
PC(13C)/PS(2D/*)
PC(13C)/PS(12C/*)
18
10
1
delay, in rotor cycles
200
100
0
δc

Figure 4

Figure 5


POLYCARBONATE ROTATIONAL ECHOS
AMPLITUDE
PC(13C)
TIME
PC(13C)/*
TIME

TECHNICAL REPORT DISTRIBUTION LIST - GENERAL

Office of Naval Research (2)
Chemistry Division, Code 1113
800 North Quincy Street
Arlington, Virginia 22217-5000

Dr. Robert Green, Director (1)
Chemistry Division, Code 385
Naval Weapons Center
China Lake, CA 93555-6001

Commanding Officer (1)
Naval Weapons Support Center
Dr. Bernard E. Douda
Crane, Indiana 47522-5050

Chief of Naval Research (1)
Special Assistant for Marine Corps Matters
Code 00MC
800 North Quincy Street
Arlington, VA 22217-5000

Dr. Richard W. Drisko (1)
Naval Civil Engineering Laboratory
Code L52
Port Hueneme, CA 93043

Dr. Bernadette Eichinger (1)
Naval Ship Systems Engineering Station
Code 053
Philadelphia Naval Base
Philadelphia, PA 19112

David Taylor Research Center (1)
Dr. Eugene C. Fischer
Annapolis, MD 21402-5067

Dr. Sachio Yamamoto (1)
Naval Ocean Systems Center
Code 52
San Diego, CA 92152-5000

Dr. James S. Murday (1)
Chemistry Division, Code 6100
Naval Research Laboratory
Washington, D.C. 20375-5000

Dr. Harold H. Singerman (1)
David Taylor Research Center
Code 283
Annapolis, MD 21402-5067

In preparing the general distribution list for the TECHNICAL REPORTS, the address for the Defense Technical Information Center (DTIC) was omitted. When technical reports are prepared, two high quality copies should be forwarded to:

Defense Technical Information Center
Building 5, Cameron Station (2)
Alexandria, VA 22314